



ALKALI RESISTANT PRIMER

160 g/m²

WB ARP 02

	Weight, %	Suppliers
Water	3.60	
PLIOTEC® SA40	20.80	OMNOVA SOLUTIONS
Orotan 731 A ER	0.40	Dow Coating Materials
AMP 90	0.20	Angus - Dow Chemical Company
Byk 023	0.10	Byk Chemie
Tioxide TR92	7.40	Huntsman Pigments Division
Durcal 5	13.60	Omya
Durcal 10	15.20	Omya
Steopac	7.00	Imerys Luzenac
<i>Disperse at high speed then add</i>		
PLIOTEC® SA40	26.50	OMNOVA SOLUTIONS
<i>Add under stirring</i>		
Dowanol DPM	0.80	Dow Chemical Company
Dowanol DPnB	0.80	Dow Chemical Company
Dowanol TPnB	2.90	Dow Chemical Company
Byk 023	0.10	Byk Chemie
Acrysol RM5000	0.20	Dow Coating Materials
Acrysol ASE 60 ER (20% in water)	0.40	Dow Coating Materials

PVC	39.6%	Specific Gravity	1.41
Volume Solids	53.4%	VOC (EU)	25 g/L
Weight Solids	66.1%	Viscosity @ 10000 s ⁻¹	0.21 Pa.s

Directive 2004/42/EC	Cat. A/g maximum VOC content: 30 g/L (2010)
-----------------------------	---

NOTE: Although the data supplied above is believed to be accurate, each user is advised to make an independent determination as to whether the described Product(s) is/are appropriate for a particular use or application, whether such use will comply with all applicable laws or regulations, or whether such use will infringe the intellectual property rights of third parties.

www.omnova.com



Americas

World Headquarters
175 Ghent Road
Fairlawn, OH 44333
United States

PHONE +1 330 869-4323

FAX +1 330 869-4338

CUSTOMER SERVICE +1 888 253-5454

EMAIL pccustserv@omnova.com

Europe / Middle East / Africa / India

14, avenue des Tropiques
Z.A. de Courtaboeuf 2 - Villejust
91955 Courtaboeuf Cedex

France

PHONE +33 (0) 1 69 29 27 00

FAX +33 (0) 1 69 29 27 01

Asia

Unit 09-11, 7th Floor,
Greenland Riverside International Center
596 Long Hua Middle Road, Xu Hui District
Shanghai, 200032, China

PHONE +86 (21) - 6473 2525

FAX +86 (21) - 5421 1766